

U.S. Patent Application Serial No. 10/073,877  
Amendment dated November 21, 2003  
Reply to OA of August 22, 2003

**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

Claim 1 (Canceled).

Claim 2 (Currently Amended): The process as claimed in claim [[1]] 22, wherein said etchant further contains at least one of water and hydrogen peroxide solution.

Claim 3 (Currently Amended): The process as claimed in claim [[1]] 22, wherein said etchant has a composition tailored such that, in said step c), an etching rate of said stepped structure and an etching rate of said second III-V compound semiconductor layer of said composite structure, are substantially equal.

Claim 4 (Original): The process as claimed in claim 3, wherein said step a) is performed such that said second III-V compound semiconductor layer has a thickness that is substantially equal to a product of an etching rate of the InP layer using said etchant and an etching time of said step c).

Claim 5 (Currently Amended): The process as claimed in claim [[1]] 22, wherein said etchant has a composition tailored such that, in said step c), an etching rate of said stepped structure

U.S. Patent Application Serial No. 10/073,877  
Amendment dated November 21, 2003  
Reply to OA of August 22, 2003

is lower than an etching rate of said second III-V compound semiconductor layer of said composite structure.

Claim 6 (Canceled).

Claim 7 (Currently Amended): The process as claimed in claim [[6]] 24, wherein said ~~further~~ second etchant further contains at least one of water and hydrogen peroxide solution.

Claim 8 (Original): The process as claimed in claim 7, wherein the relationship between an etching time  $T_1$  in said step c) and an etching time  $T_2$  in said step d) is determined in accordance with an equation:

$$(V_2 - V_1) \times T_1 = (V_3 - V_4) \times T_2,$$

where  $V_1$  is an etching rate of the InP layer in said step c);

$V_2$  is an etching rate of said second III-V compound semiconductor layer in said step c);

$V_3$  is an etching rate of the InP layer in said step d); and

$V_4$  is an etching rate of said second III-V compound semiconductor layer in said step d).

Claim 9 (Currently Amended): The process as claimed in claim [[1]] 22, wherein said etchant has a composition tailored such that, in said step c), an etching rate of said stepped structure

U.S. Patent Application Serial No. 10/073,877  
Amendment dated November 21, 2003  
Reply to OA of August 22, 2003

is greater than an etching rate of said second III-V compound semiconductor layer of said composite structure.

Claim 10 (Currently Amended): The process as claimed in claim 9, wherein said ~~further~~ etchant further contains at least one of water and hydrogen peroxide solution.

Claim 11 (Canceled).

Claim 12 (Currently Amended): The process as claimed in claim [[11]] 25, wherein the relationship between an etching time  $T_1$  in said step c) and an etching time  $T_2$  in said step d) is determined in accordance with an equation:

$$(V_1 - V_2) \times T_1 = (V_4 - V_3) \times T_2,$$

where  $V_1$  is an etching rate of the InP layer in said step c);

$V_2$  is an etching rate of said second III-V compound semiconductor layer in said step c);

$V_3$  is an etching rate of the InP layer in said step d); and

$V_4$  is an etching rate of said second III-V compound semiconductor layer in said step d).

Claims 13-14 (Canceled).

U.S. Patent Application Serial No. 10/073,877  
Amendment dated November 21, 2003  
Reply to OA of August 22, 2003

Claim 15 (Currently Amended): The process as claimed in claim [[14]] 26, wherein said further second etchant further contains at least one of water and hydrogen peroxide solution.

Claim 16 (Original): The process as claimed in claim 15, wherein the relationship between an etching time  $T_1$  in said step c) and an etching time  $T_2$  in said step e) is determined in accordance with an equation:

$$V_1 \times T_1 = (V_4 - V_3) \times T_2,$$

where  $V_1$  is an etching rate of the InP layer in said step c);

$V_3$  is an etching rate of the InP layer in said step e); and

$V_4$  is an etching rate of said second III-V compound semiconductor layer in said step e).

Claim 17 (Currently Amended): The process as claimed in claim [[1]] 22, wherein, after said step c), said stepped structure of said etched structure, is provided with a planarized surface formed of a (100), (011) or (0-1-1) surface.

Claim 18 (Original): The process as claimed in claim 17, wherein said planarized surface is substantially flush with the surface of said first III-V compound semiconductor layer.

U.S. Patent Application Serial No. 10/073,877  
Amendment dated November 21, 2003  
Reply to OA of August 22, 2003

Claim 19 (Currently Amended): The process as claimed in claim [[1]] 22, wherein, after said step c), said stepped structure of said etched structure, is provided with a planarized surface near a (100), (011) or (0-1-1) surface.

Claim 20 (Currently Amended): The process as claimed in claim [[1]] 22, wherein said second III-V compound semiconductor layer has a composition ~~chosen~~ selected from [[a]] the group consisting of InP, InGaAs, InAs, InGaP, InGaAsP and GaInNAs.

Claim 21 (Currently Amended): The process as claimed in claim [[1]] 22, wherein said first III-V compound semiconductor layer has a composition ~~chosen~~ selected from [[a]] the group consisting of InGaAs and InGaAsP.

Claim 22 (New): A process of manufacturing a semiconductor device, comprising the steps of:

a) forming a stacked structure of a first III-V compound semiconductor layer containing In and having a composition different from InP and a second III-V compound semiconductor layer containing In, said second III-V compound semiconductor layer being formed directly on said first III-V compound semiconductor layer, where said second III-V compound semiconductor layer is disposed above said first III-V compound semiconductor layer;

b) growing an InP layer at regions adjacent said stacked structure to form a stepped structure of InP, said stepped structure and said stacked structure together defining a composite structure; and

c) wet-etching said composite structure using an etchant containing hydrochloric acid and acetic acid, to produce an etched structure.

Claim 23 (New): The process of claim 22, said step of forming, further comprising:

forming a pattern covering said second III-V compound semiconductor layer on said stacked structure, wherein said second III-V compound semiconductor layer is protected by said pattern upon wet-etching said composite structure.

Claim 24 (New): The process as claimed in claim 5, further comprising the step of:

d) second wet-etching said etched structure using a second etchant containing hydrochloric acid and acetic acid to produce a planarized structure, said second etchant having a composition tailored such that an etching rate of said stepped structure is greater than an etching rate of said second III-V compound semiconductor layer, of said etched structure.

Claim 25 (New): The process as claimed in claim 9, further comprising the step of:

d) second wet-etching said etched structure using a second etchant containing hydrochloric acid and acetic acid to obtain a planarized structure, said second etchant having a composition

U.S. Patent Application Serial No. 10/073,877  
Amendment dated November 21, 2003  
Reply to OA of August 22, 2003

tailored such that an etching rate of said stepped structure is smaller than an etching rate of said second III-V compound semiconductor layer, of said etched structure.

Claim 26 (New): The process as claimed in claim 23, further comprising the step of:

d) removing said pattern after said wet-etching; and

e) second wet-etching said etched composite using a second etchant containing hydrochloric acid and acetic acid to produce a planarized structure, said second etchant having a composition tailored such that an etching rate of said stepped structure is smaller than an etching rate of said second III-V compound semiconductor layer, of said etched structure.